

Titalon 4300GF

RESIN : POLYAMIDE 46 RESIN

PRODUCT DESCRIPTION : PA 46 REINFORCED WITH 30% GLASS FIBER, HIGH STRENGTH, HIGH HEAT RESISTANCE.

COLOR No.: VN01

Properties	Unit	method	Value
Color	-	-	Natural
Density	g/cm ³	ISO 1183	1.36
Tensile strength	MPa	ISO	180
Tensile Elongation		527-1,2	>2
Flexural strength	MPa	ISO 178	290
Flexural modulus			10000
Charpy impact strength(notched)	kJ/m ²	ISO	10
		179/1eA	
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	285
Volume resistivity	Ω•cm	IEC 60093	1×10 ¹²
Surface resistivity	Ω		1×10 ¹²
Flammability		UL 94	HB
Mold shrinkage	%	50x80x3 mmt	0.3~0.7
MOLDING CONDITION			
MOLDING CONDITION	°C	Drying	110x 4Hrs
		Melt Temperature	280~310
		Mold Temperature	80~120
	%	Inject. Pressure	30~70
Inject. Velocity		30~60	

*All property values shown in this data sheet are the representative values and not minimum value of this material.