

Titalon 5200CF

RESIN : POLYCARBONATE (PC)

PRODUCT DESCRIPTION : 20% CARBON FIBER, HIGH STRENGTH, GOOD
CONDUCTIVITY.

COLOR No.: VB01

Properties	Unit	method	Value
Color	-	-	Black
Density	g/cm ³	ISO 1183	1.27
Tensile strength	MPa	ISO	150
Tensile Elongation		527-1,2	2
Flexural strength	MPa	ISO 178	200
Flexural modulus			10000
Charpy impact strength(notched)	kJ/m ²	ISO	8
		179/1eA	
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	140
Volume resistivity	Ω•cm	IEC 60093	1×10 ^{3~5}
Surface resistivity	Ω		1×10 ^{3~5}
Flammability		UL 94	HB
Mold shrinkage	%	50x80x3 mmt	0.2~0.5
MOLDING CONDITION			
MOLDING CONDITION	°C	Drying	120x 4Hrs
		Melt Temperature	270~300
		Mold Temperature	80~120
	%	Inject. Pressure	40~70
Inject. Velocity		20~60	

*All property values shown in this data sheet are the representative values and not minimum value of this material.