



## GF920

RESIN : POLYACETAL (POM) RESIN

PRODUCT DESCRIPTION : ACETAL COPLOYMER REINFORCED WITH 20% GLASS FIBER.

COLOR No.: VN01

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm <sup>3</sup>	ISO 1183	1.54
Tensile strength	MPa	ISO	115
Tensile Elongation		527-1,2	>2
Flexural strength	MPa	ISO 178	175
Flexural modulus			6000
Charpy impact strength(notched)	kJ/m <sup>2</sup>	ISO 179/1eA	8
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	158
Volume resistivity	Ω•cm	IEC 60093	1×10 <sup>14</sup>
Surface resistivity	Ω		1×10 <sup>14</sup>
Flammability	class	UL 94	HB
UL yellow card file number	-	-	E525438
Mold shrinkage	%	50x80x3 mmt	0.6~1.0
MOLDING CONDITION			
	°C	Drying	100x 3Hrs
		Melt Temperature	170~200
		Mold Temperature	60~100
	%	Inject. Pressure	30~70
		Inject. Velocity	20~50

\*All property values shown in this data sheet are the representative values and not minimum value of this material.